



THE HOOK AND LOOP FASTENER

V24 PEEK/NOMEX QUALITY

PRODUCT SUMMARY

Material Composition	48% Polyetheretherketone (PEEK®) 52% m-Aramid (Nomex®)	
Widths Available	16, 30, 38 mm	
Colours Available	Natural Only	
Packaging	Hook and Loop tapes sold separately on 25 metre rolls. Special requirements are also available.	

SPECIAL PROPERTIES

Flammability	Sclf-Extinguishing		
Limiting Oxygen Index (LO1)	29		
Thermal Performance	Excellent		
Temperature Range	−50°C to +200°C		

These products conform to the requirements of:

- ABD 0031 issue A.
- CAA Spec. 8 Issue 2.
- FMVSS 302 and associated specifications.

FASTENER PERFORMANCE

SHEAR STRENGTH	BS 7271:1990	PEEL STRENGTH	BS 7271;1990
Initially	7.0 N/cm ²	Initially	1.2 N/cm
After 500 Cycles	5.0 N/cm ²	After 500 Cycles	0.8 N/cm
After 2000 Cycles	4.3 N/cm ²	After 2000 Cycles	0.7 N/cm
After Laundering	6.8 N/cm ²	After Laundering	1.1 N/cm
10.0		2.0	



V24 PEEK/NOMEX QUALITY

P:03

OTHER PROPERTIES

CHEMICAL RESISTANCE		
Reagent	Resistance	
10% Sulphuric Acid	Excellent	
50% Sulphuric Acid	Moderate	
10% Nitric Acid	Excellent	
50% Nitric Acid	Poor	
30% Hydrochloric Acid	Good	
10% Phosphoric Acid	Excellent	
75% Phosphoric Acid	Fair	
10% Sodium Hydroxide	Excellent	
50% Sodium Hydroxide	Poor	
Octane	Excellent	
Bleach	Good	

TYPICAL APPLICATIONS	Clothing:-	- Heat Protective Clothing.
		- Industrial Protective Clothing
		- High Performance Clothing:
		- Fire Fighters.
		- Racing Drivers.

WARRANTY

All Information, recommendations and descriptive material about the product are based upon research and believed to be reliable, but do not constitute a warranty. All products are sold with the understanding that the purchaser will independently determine the suitability of the material for their own purpose.

No salesperson, representative or agent is authorised to give any warranty, guarantee or make any representation to the foregoing.



SELECTUS LIMITED BIDDULPH, STOKE-ON-TRENT, ST87RH **ENGLAND**

Telephone: 01782 522316. Fax: 01782 522574.



