

ERTALON® NYLATRON®

Polyamides (PA)

Within the polyamides, commonly referred to as "nylons", we distinguish different types. The most important ones are: PA 6, PA 66, PA 11 and PA 12. The differences in physical properties which exist between these types are mainly determined by the composition and the structure of their molecular chains.

Main characteristics:

- high mechanical strength, stiffness, hardness and toughness
- good fatigue resistance
- high mechanical damping ability
- good sliding properties
- excellent wear resistance
- good machinability

EXTRUDED PRODUCTS

ERTALON 6 SA (PA 6) natural (white) / black

This material offers an optimal combination of mechanical strength, stiffness, toughness, mechanical damping properties and wear resistance. These properties, together with a favourable electrical insulating ability and a good chemical resistance make ERTALON 6 SA a "general purpose" grade for mechanical construction and maintenance.

ERTALON 66 SA (PA 66) natural (cream) / black

Material with a higher mechanical strength, stiffness, heat and wear resistance than ERTALON 6 SA. It also has a better creep resistance but its impact strength and mechani-

cal damping ability are reduced. Well suited for machining on automatic lathes.

ERTALON 4.6 (PA 4.6) (reddish brown)


Compared with the conventional nylons, ERTALON 4.6 (STANYL®) features a better retention of stiffness and creep resistance over a wide range of temperatures as well as a superior heat ageing resistance. Therefore, applications for ERTALON 4.6 are situated in the "higher temperature area" (80 - 150°C) where stiffness, creep resistance, heat ageing resistance, fatigue strength and wear resistance of PA 6, PA 66, POM and PET fall short.

ERTALON 66-GF30 (PA 66-GF30) (black)

Compared with virgin PA 66, this 30% glass fibre reinforced and heat stabilised nylon grade offers increased strength, stiffness, creep resistance and dimensional stability whilst retaining an excellent wear resistance. It also allows higher max. service temperatures.

NYLATRON GS (PA 66 + MoS₂) (grey-black)

The addition of MoS₂ renders this material somewhat stiffer, harder and dimensionally more stable than ERTALON 66 SA, but results in some loss of impact strength. The nucleating effect of the molybdenum disulphide results into an improved crystalline structure enhancing bearing and wear properties.



ERTALON 4.6 ERTALON 66-GF30

round rods

Diameters (mm)	Tolerances on the diameters (mm)		Weights (1) - (kg/m)	
			ERTALON 4.6	ERTALON 66-GF30
			40005500	40004500
5	+ 0.1	+ 0.4	○ 0.026	-
6			○ 0.037	-
8			○ 0.065	○ 0.072
10	+ 0.1	+ 0.5	● 0.100	● 0.111
12			○ 0.146	● 0.163
15			● 0.225	● 0.250
16	+ 0.2	+ 0.7	○ 0.256	● 0.283
18			○ 0.322	● 0.355
20			● 0.395	● 0.436
22			○ 0.480	○ 0.530
25	+ 0.2	+ 0.9	● 0.615	● 0.680
28			○ 0.770	○ 0.850
30			● 0.880	● 0.970
32	+ 0.2	+ 1.1	○ 1.01	○ 1.11
36			○ 1.27	● 1.40
40			● 1.57	● 1.72
45	+ 0.3	+ 1.3	○ 1.99	● 2.18
50			● 2.45	● 2.68
60	+ 0.3	+ 1.6	● 3.52	● 3.86
70			-	● 5.22
80	+ 0.4	+ 2	-	● 6.84
90	+ 0.5	+ 2.2	-	○ 8.66
100	+ 0.6	+ 2.5	-	● 10.70
110	+ 0.7	+ 3	-	○ 13.00
120	+ 0.8	+ 3.5	-	● 15.50
125			-	○ 16.80
130	+ 0.9	+ 3.8	-	● 18.20
140			-	○ 21.05
150	+ 1	+ 4.2	-	● 24.20
180	+ 1.2	+ 5	-	● 34.85
200	+ 1.3	+ 5.5	-	● 42.95
Standard lengths (mm)			Tolerance on the lengths (%)	
1000			0	
3000			+ 3	
Non-standard lengths (cut-to-size) : ○				

(1) : average production weights

- : standard item (available from stock or with short delivery time)
- : non-standard item (manufactured on request)
- : not available

PRODUCT CODE

Thicknesses (mm)	Tolerances (1) on the thicknesses (mm)		Weights (2) - (kg/m)	
			natural	black
			40004004	40004104
8	+ 0.2	+ 0.9	■ 6.15	□ 6.15
10			■ 7.59	□ 7.59
12			■ 9.28	□ 9.28
15			■ 11.45	□ 11.45
16			■ 12.15	□ 12.15
20			■ 15.05	□ 15.05
25	+ 0.3	+ 1.5	■ 18.65	□ 18.65
30			■ 22.65	□ 22.65
35			■ 26.25	□ 26.25
40			■ 29.85	□ 29.85
45			□ 33.45	□ 33.45
50			■ 37.05	□ 37.05
60	+ 0.5	+ 2.5	■ 44.60	□ 44.60
70			□ 51.80	□ 51.80
80	+ 0.5	+ 5	□ 59.55	□ 59.55
90			□ 66.75	□ 66.75
100			□ 73.95	□ 73.95
Standard sizes (mm)			Tolerances (1) on width and lengths	
610 x 1000			Width : + 5 mm + 25 mm	
610 x 3000			Lengths : 0 + 3 %	
Cut-to-size products : □				

(1) : tolerances according to DIN 16986

(2) : average production weights

■ : standard item (available from stock or with short delivery time)

□ : non-standard item (manufactured on request)

PRODUCT CODE

ERTALON 4.6

ERTALON 66-GF30

Thicknesses (mm)	Tolerances on the thicknesses (mm)		Weights (1) - (kg/m)		
			ERTALON 4.6		ERTALON 66-GF30
			width = 500 mm	width = 610 mm	width = 625 mm
			40005504		40004504
10	+ 0.2	+ 0.9	-	■ 8.05	■ 8.84
15	+ 0.3	+ 1.5	-	■ 12.15	■ 13.30
20			-	■ 15.90	■ 17.50
25			-	■ 19.70	■ 21.70
30			-	■ 24.00	■ 26.40
40	+ 0.5	+ 2.5	-	■ 31.55	■ 34.80
50			■ 32.20	(2) 39.10	■ 43.15
60	+ 0.5	+ 3.5	-	-	■ 51.95
70			-	-	□ 60.35
80	+ 0.5	+ 5	-	-	■ 69.35
90			-	-	□ 77.70
100			-	-	■ 86.10
Standard sizes (mm)			Tolerances on widths and lengths		
ERTALON 4.6	ERTALON 66-GF30		Widths : + 5 mm + 25 mm Lengths : 0 + 3 %		
500/610 x 1000	625 x 1000				
500/610 x 3000	625 x 3000				
Cut-to-size products : □					

(1) : average production weights

(2) : in development. Please consult us.

■ : standard item (available from stock or with short delivery time)

□ : non-standard item (manufactured on request)

- : not available

PRODUCT CODE