



Farnell: 703-4155

Devcon 11762

DEVCON LIMITED

A subsidiary of **ITW** Inc.

BAY 150, SHANNON INDUSTRIAL ESTATE, SHANNON, CO. CLARE, IRELAND. TELEPHONE 061-471299 FAX 061-471285 TELEX 72186

FOR MAINTENANCE AND TOOLING

OUR REFERENCE

YOUR REFERENCE

BRUSHABLE CERAMIC BLUE

Technical Data

MIXED VISCOSITY	32 Pa.s
VOLUME SOLIDS	100 %
CURED DENSITY	1.69 g/cc
POT LIFE AT 24°C	40 minutes
COMPRESSIVE STRENGTH (ASTM D695).....	105 MPa
ADHESIVE TENSILE SHEAR (ASTM D1002).....	13.8 MPa
CURED HARDNESS SHORE D (ASTM D2240).....	90
DIELECTRIC STRENGTH (ASTM D149).....	15 kV/mm
COVERAGE	1.2 m ² /kg at 0.5 mm
TYPICAL BRUSH COAT THICKNESS	0.25 - 0.5 mm
TEMPERATURE: Wet 65°C Dry 75°C	